

# Product Selector Guide

Resin System	Description	Outlife at 70°F (Days)	Initial Cure Temp (°F)	Initial Cure Time (Hours)	Post Cure Option	Max Tg Onset* (°F - DMA)	Max Tg Peak* (°F - DMA)	Toughened	Standard Process	Typical Application Areas
<strong>TOOLING PREPREG — Low Temperature Cure</strong>										
LTC102	Epoxy Carbon/Glass Tooling	3	85 – 150	45 – 5	Yes	417	450	No	Autoclave	Commercial low temp tooling
LTC210-1	Epoxy Carbon/Glass Tooling	4	115 – 160	40 – 4	Yes	399	446	No	Autoclave	Commercial low temp tooling
LTB310-1	Epoxy Carbon/Glass Tooling - 30% bio-based	4	115 – 160	40 – 4	Yes	394	446	No	Autoclave	Commercial low temp epoxy tooling with 30% bio content
LTC216-3	Epoxy Carbon/Glass Tooling	8	115 – 160	50 – 5	Yes	424	468	No	Autoclave	Aerospace low temp tooling
LTC400	Epoxy Long Outlife Tooling	30	150 – 175	20 – 6	Yes	405	442	No	Autoclave	Extra long outlife, low temp Aerospace tooling
OTS65	Epoxy Oven Cure Tooling	Up to 21	150 – 195	Consult Data Sheet	Yes	264	289	No	Oven	Out of Autoclave tooling & structures
BMI-1SC	BMI Tooling & Component	30	365	2	Yes	662	671	No	Autoclave	High temp, high durability Aerospace Tooling
<strong>ADHESIVE FILM</strong>										
MTFA500	Adhesive Film	30	175 – 250	16 – 1	No	286	302	Yes	Autoclave	General purpose film adhesive
VTFA400	Adhesive Film	21	150 – 250	16 – 1	No	275	297	Yes	Autoclave	General purpose film adhesive with versatile cure
MTFA400	Adhesive Film, High Temperature Service	30	175 – 300	16 – 1	Yes	338	374	Yes	Autoclave	General purpose, higher service temp
<strong>COMPONENT PREPREG — Low to Medium Temperature Cure</strong>										
LTC250-2XL	Low Temp Cure	5	120 – 165	40 – 4	Yes	266	291	Yes	Autoclave/Oven	Lower temp cure with good toughness and visual clarity. Excellent for low cost prototypes
MTC510	Med Temp Cure, Cosmetic & General Purpose	30	175 – 250	16 – 1	No	268	298	Yes	Autoclave	General purpose system also with excellent optical clarity for cosmetic carbon parts. Low viscosity version available
MTE500	Next Generation Multi-Purpose Component System	60	250	1	No	284	311	Yes	Autoclave	General purpose system with optimised handling characteristics for the production of the highest quality visual parts
MTC275	Med Temp Cure, Out of Autoclave	30	175 – 250	16 – 1	No	250	275	Yes	Autoclave/Oven	General purpose system also with excellent optical clarity for cosmetic carbon parts. Can process OOA
MTC475	Med Temp Cure, High Service Cosmetic	30	175 – 250	16 – 1	Yes	374	403	Yes	Autoclave	Higher service temp system with good visual finish
MTC580 Series	Med Temp Cure, Flow Controlled	30	185 – 250	16 – 1	Yes	311**	336**	Yes	Autoclave/Oven/Press	General purpose system with optimised flow control and high toughness. Core bondable. Snap-cure versions available
MTC400-1	Med Temp Cure, High Temp Structural	30	175 – 275	16 – 1	Yes	405	435	Yes	Autoclave/Oven/Press	Higher service temp (typically up to 302°F) structural components in Automotive and Motorsport
MTC412	Med Temp Cure, High Temp Service OOA	28	175 – 300	16 – 1	Yes	338	374	Yes	Autoclave/Oven	High service temp and Out of Autoclave processing typically for Aerospace applications
<strong>COMPONENT PREPREG — Versatile Temperature Cure</strong>										
VTC401	General Purpose, Fast Cure Component Core Bondable	21	150 – 285	16 – 15 mins	No	266	282	Yes	Autoclave/Oven/Press	Versatile system. Low temp cure on lower cost large structures, but also with high temp "snap" cure capability
VTC410	General Purpose, Fast Cure Component	21	150 – 285	16 – 15 mins	Yes	374	403	Yes	Autoclave/Oven/Press	Versatile system. Low temp cure for lower cost, larger structure with increased service temperature
VTC212	Surfacing System, Out of Autoclave	21	150 – 250	16 – 1	Yes	275	284	Yes	Oven	Versatile system with good Out of Autoclave processing for high quality surface finishes
OPS75	Oven Panel System	Up to 21	150 – 265	Consult Data Sheet	No	284	320	Yes	Autoclave/Oven	Automotive body panels with excellent retained surface finish once environmentally cycled
APS75	Autoclave Panel System	21	150 – 265	Consult Data Sheet	Yes	338	376	Yes	Autoclave	Automotive body panels with higher service temp
<strong>COMPONENT PREPREG — High Service Temperature</strong>										
HTC400	High Temp Cure, High Service Temp	30	355	2	No	505	522	Yes	Autoclave	High service temp Automotive and Aerospace structures
CEL100-1	Cyanate Ester, Low Temp Cure	2	160 – 195	22 – 6	Yes	565	592	No	Autoclave	High service temp with a required postcure, suitable for Automotive components
CEM160	Cyanate Ester, High Service Temp, Available on UD reinforcements	Up to 21	250 – 275	3 – 2	Yes	527	572	No	Autoclave	High service temp Automotive and Space components with low-outgassing requirements
<strong>COMPONENT PREPREG — Flame Retardant</strong>										
FRVC411	Flame Retardant, Core Bondable	21	150 – 285	16 – 15 mins	Yes	311	349	Yes	Autoclave/Oven/Press	Flame retardant (can meet UL94 V0) Aerospace and Automotive structures
MTC510-1FRB	Flame Retardant, Med Temp Cure	30	175 – 250	16 – 1	No	266	298	Yes	Autoclave	General purpose flame retardant system
PS200	Flame Retardant, Bio-based	21	210 – 265	3 – 1	Consult SHD	536	626	No	Autoclave/Press – Contact SHD	Bio-derived, highly flame retardant system for fire containment applications such as battery enclosures
FR308P	Flame Retardant, Bio-based	21	210 – 265	3 – 1	Consult SHD	361	410**	No	Autoclave/Press – Contact SHD	Bio-derived, highly flame retardant system for interior structures typically to replace phenolic resins

**Disclaimer:** Technical advice, instruction, data or recommendation, whether verbal or in writing, is given in good faith. The SHD company providing any such advice gives no warranty or guarantee, whether express or implied, in relation to such advice. Customers must carry out their own tests and assessments as necessary in order to determine the quality and suitability of the product for their particular application and circumstances. Such testing should be performed under conditions identical to those to which the final component/product may be subjected. Values listed in any SHD document are for typical properties of the product or substance in question and are not intended to be used in establishing either statistical specifications nor engineering basis values. They do not constitute either minimum or maximum values for the product or substance in question. To view our Terms and Conditions online, please visit [www.shdcomposites.com/terms-and-conditions](http://www.shdcomposites.com/terms-and-conditions).

SHD Composites continuously reviews and updates its Product Selector Guide and Technical Data Sheets. Please ensure that you have the current version, by contacting your SHD Composites sales contact and quoting the issue date.

\* Tg and service temperatures quoted in this Product Selector Guide are maximum values, possibly achieved after a post cure cycle depending on the product. Please consult Technical Data Sheets for details.

\*\* Typical suggested maximum service temperature of 180°F.

\*\*\* FR308P can potentially reach a Peak Tan Θ Tg above 450°F after high temperature post-cure cycles.

[www.shdcomposites.com](http://www.shdcomposites.com)  
+1 (704) 626 6876

us-sales@shdcomposites.com

Issued 1st August 2025

SHDUS/MISC/918 – Iss 3